

This listing of claims will replace all prior versions, and listings, of claimed in the application

Listing of claims:

1 (currently amended). A CRT panel ~~glass~~ which does not substantially contain PbO, which contains, in mass percent, 9-9.5 % SrO, 8.5-9 % BaO, 0.1-2.5 % ZrO₂ and 0.1-2 % TiO₂, with SrO/(SrO+BaO) being 0.50-0.53, and which has an X-ray absorption coefficient of 28.0^{-1} or more at 0.6 Å.

2 (currently amended). A CRT panel ~~glass~~ as claimed in claim 1, wherein the content of SrO is 9.1-9.4 % in mass percent.

3 (currently amended). A CRT panel ~~glass~~ as claimed in claim 1, wherein the content of BaO is 8.6-8.9 % in mass percent.

4 (currently amended). A CRT panel ~~glass~~ which does not substantially contain PbO, which contains, in mass percent, 50-70 % SiO₂, 0-4 % Al₂O₃, 0-4 % MgO, 0-4 % CaO, 9-9.5 % SrO, 8.5-9 % BaO, 0-2 % ZnO, 5-10 % Na₂O, 5-10 % K₂O, 0.1-2.5 % ZrO₂, 0.1-2 % TiO₂, 0-2% CeO₂, 0-2 % Sb₂O₃, and 0-2 % P₂O₅, with SrO/(SrO+BaO) being 0.50-0.53, and which has an X-ray

absorption coefficient of 28.0 cm^{-1} or more at 0.6 \AA .

5 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of SiO_2 is 53-67 % in mass percent.

6 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of Al_2O_3 is 3 % or less in mass percent.

7 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of MgO is 2 % or less in mass percent.

8 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of CaO is 2 % or less in mass percent.

9 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of SrO is 9.1-9.4 % in mass percent.

10 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of BaO is 8.6-8.9 % in mass percent.

11 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of ZnO is 1 % or less in mass percent.

12 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of Na₂O is 6-9 % in mass percent.

13 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of K₂O is 6-9 % in mass percent.

14 (canceled).

15 (canceled).

16 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of CeO₂ is 0.1-2 % in mass percent.

17 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of Sb₂O₃ is 1 % or less in mass percent.

18 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the content of P₂O₅ is 1 % or less in mass percent.

19 (currently amended). A CRT panel ~~glass~~ as claimed in claim 4, wherein the coloring agent is added up to 0.3 % in mass percent.